

	<h2>ULTRA – MIX</h2>
	<p>Cement based finishing plaster</p> <p style="text-align: right;">EN 998-1 </p>

Description

ULTRA-MIX is cement based finishing plaster, reinforced with microfibers acrylic copolymers, for interior and exterior surfaces. Suitable for application over conventional building surfaces, such as cement renderings, fair-face concrete, concrete blocks etc.

Technical Specifications

Density	: ~1.15 kg/L
Density of fresh mortar	: ~1.60 kg/L
Mixing ratio (water / ULTRA-MIX)	: ~8-8,5L / 25kg
Substrate temperature	: +5°C min. / +35°C max.
Ambient temperature	: +5°C min. / +35°C max.
Reaction to fire	: Class A1
Compressive strength	: CS IV
Flexural strength	: $\geq 2 \text{ N/mm}^2$
Adhesion strength	: $0,6 \text{ N/mm}^2 - \text{FP:A}$
Water absorption	: W1
Water vapour permeability coefficient	: $\mu 7$
Thermal conductivity (λ_{dry})	: $\leq 0,44 \text{ W/mk}$ (tab. mean value, P=50%)
Pot life	: at least 3 hours at 23°C
<u>Consumption:</u> 2.9 - 3.5 kg/m ² of ULTRA-MIX for a layer thickness of 2-3mm	

Instructions for Use

SURFACE PREPARATION

All substrates should be clean, free of dust, oil, residues of other building materials, etc. before applying the plaster. The substrate must be sprayed with water, especially in periods of hot weather. In such case, surface film should be allowed to dry after spraying, so as not to inhibit adhesion of the mortar.

MIXING

All equipment and containers should be clean, free of dust, residues of previous mixtures and/or other building materials, etc. so as to not adversely affect the setting time and the mechanical properties of the product.

Depending on the desired density and consistence, mix 25kg (1 bag) of **ULTRA-MIX** with 8-8,5L of clean water. While stirring, add the proportional quantity of dry powder.

Use a low speed mechanical stirrer for the preparation of the mortar. Mix for at least 3 minutes, until a homogeneous, free of lumps mixture is obtained and the desired consistency is achieved.

The pot life of the mixture is at least 3 hours, if stirred periodically. In case the mixture has started to set before it's used, then dispose immediately without using it. In any case, do not add additional water for remixing and/or for improving its workability.



APPLICATION CONDITIONS

Use only at temperatures between +5°C and +35°C. During winter or periods of low temperatures (5-10°C), it is advisable that warm water (approx. 30°C), is used for the mixing and if possible, the application to be performed during noontime. On the contrary, use cool water (approx. 20°C), for the mixing during summer and generally at ambient temperatures exceeding or expected to exceed 35°C.

APPLICATION

Apply **ULTRA-MIX** in two layers of 1mm approximately each. The first layer (scratch coat) will fill holes and irregularities of the substrate, while the second will add thickness to the final coating. The total thickness of the coating shall not exceed 2-3mm. Apply the second layer only after the first one has set. The surface may either be floated (plastic or sponge float) or made smooth with the edge of a rectangular steel trowel (wall leveling saving).

Take special care that, starting 24 hours after it's been applied, the finished plaster is periodically sprayed with water for up to 2-3 days, especially during hot and/or windy weathers, or generally when intense evaporation of the mixing water is likely to occur.

DECORATION

Ideally, **ULTRA-MIX** should be allowed to cure for at least 2-3 weeks before decorating. For better results, it is advised to sand the final surface before decoration. Before being decorated, surface should be smoothed using sandpaper and primed with either Peletico's EcoPrimer or Sherwin-Williams® ProMar® Masonry Conditioner (see note 1).

Final surface can be decorated using emulsion paints, enamel paints, acrylic paints, etc. (all available from Peletico). For more information about the specifications of each of the above products, please refer to the analytical Technical Data Sheet.

CLEANING OF EQUIPMENT

Clean all tools and mixing equipment thoroughly with plenty of water after completion of work, while the plaster hasn't set. Use mechanical methods to remove hardened material.

REMARKS / LIMITATIONS

- Use only fresh, clean water for both mixing and cleaning.
- Avoid using material which was stored in open containers for a long period of time, as it may contain lumps or be contaminated.
- Never add water or new product to the mixture which has started to set, in order to improve its workability.
- Do not add cement, gypsum, sand or any other materials to the supplied product, as this will negatively affect the end results of the product.
- Avoid using the product under extreme weather conditions, such as direct sunlight and strong winds.

PACKAGING

25kg multiwall paper bags (one layer of which is made of PE-HDPE).

STORAGE / SHELF LIFE

Store under dry conditions and away from direct sunlight, in a sheltered, free from water and moisture area. Store in closed bags preferably in the original packaging, onto a pallet or generally without direct contact with the floor.

The product has a shelf life of up to 3 months from production date, when stored properly in the original, unopened bag.

- The product contains cement, which reacts as alkaline with water, moisture, sweat and/or other body fluids so it is classified as irritant. Follow normal precautions as with all cementitious materials and products.
- Harmful in contact with skin.
- Harmful if inhaled.
- Harmful if swallowed.
- May cause respiratory irritation.
- Keep out of reach of children.
- Wash body and clothes thoroughly after handling.
- Do not eat, drink or smoke when using this product.
- Wear respiratory protection.
- Please refer to Safety data Sheet for more information and advices regarding the safe handling, storage, use and disposal of the material.

Health
and Safety
Measures



Note 1: Peletico's EcoPrimer: Water based acrylic primer for interior and exterior surfaces. (See Technical Specification Sheet)

PROMAR® MASONRY CONDITIONER: Solvent based primer for interior and exterior surfaces. (See Technical Specification Sheet).

Note 2: All Technical Data provided on section "Technical Specifications " are based on laboratory trials and tests, under conditions which may significantly differ from the ambient application conditions. Therefore, the actual technical characteristics may vary due to conditions or circumstances beyond company's control.

Note 3: The information provided by our Technical Data Sheets or given by our employees, agents or distributors concerning the use of our products, is based upon extensive research and experience and are provided in good faith in order to help you.

We guarantee the consistent high quality of our products; however, as we have no control over site conditions of the executions of work, we cannot accept any liability for any loss or damage, which may arise as a result thereof.

Note 4: All cement based products, must be stored in dry sheltered places, on wooden pallets. Even under these circumstances, the products are influenced by the atmospheric moisture after a period of time. Since this period is not defined or standard, we strongly advise our customers not to use hardened products or if, generally, its quality due to storage is uncertain.

